

# X-FLOW XF40 ULTRAFILTRATION MEMBRANE

MEMBRANE ELEMENT DATASHEET

ARTICLE CODE: 2872FL395A

## **GENERAL INFORMATION**

XF40 is used for process and potable water filtration. Mode of operation is dead-end with regular backwash (permeate only) and chemically enhanced backwash. Typical applications are the filtration of surface water, large-scale drinking and process water production. The XF40 module can be utilized in Pentair's unique solution Xiga.

## **GENERAL SOLVENT RESISTANCE**

Since the resistance of the membrane to solvents strongly depends on the actual process conditions, the indications given below should only be considered as quideline.

Acids ++
Bases ++
Aliphatic alcohols +
Aliphatic hydrocarbons Halogenated hydrocarbons Polar organic solvents Oils ++

## **CLEANING CHEMICAL RESISTANCE**

## **Sodium Hypochlorite**

- Typical 200 ppm, at  $\leq$  40  $^{\circ}$ C at  $\geq$  pH 10
- Maximum 500 ppm
- 250.000 ppm hours cumulative; ≥ pH 10

## **Chlorine Dioxide**

- Typical 1 ppm, at ≤ 40 °C
- Maximum 2 ppm
- 90.000 ppm hours cumulative; pH 11

## **Hydrogen Peroxide**

- Typical 200 ppm, at ≤ 40 °C
- Maximum 500 ppm
- 350.000 ppm hours cumulative

## Note:

The above figures for oxidant contact represent the membrane resistance to each individual oxidizing agent. The total combined exposure for Sodium Hypochlorite and Chlorine Dioxide will be calculated as follows:

Combined exposure (NaOCI + CIO2) = 2.6 x Exposure to CIO2 (in ppm hours)+ Exposure to NaOCI (in ppm hours) < 250.000 ppm hours

As a good working practice and in order to maximise the lifetime of the membrane it is advised to reduce the membrane exposure to oxidising agents to a minimum. Exposure limits are also affected by temperature, pH and the presence of metals. In order not to exceed maximum exposure limits, membranes must be preserved free of any oxidising agent when the plant is stopped.

#### Acids

Hydrochloric Acid ++
Nitric Acid ++
Phosphoric Acid ++
Acetic Acid ++
Citric Acid ++

pH > 2 during filtration pH > 1 during cleaning

## Bases

Sodium Hydroxide (<4%) ++
Potassium Hydroxide (<4%) ++


pH < 12 during filtration pH < 13 during cleaning

## **MEMBRANE CHARACTERISTICS**

- Hydrophilic membrane composed of a blend of polyvinylpyrrolidone and polyethersulfone
- A nominal pore size of 20 nm
- Structure asymmetric/microporous
- High performance and a very good antifouling behaviour
- Typical permeate quality SDI<3, turbidity <0,1 NTU</li>
- Membrane filtration provides 99.9999% (LOG6) reduction of bacteria (Pseudomonas diminuta) and 99.99% (LOG 4) reduction of virus (MS2 colifages) by mechanical means. EPA Est. No. 090374-NLD-001

# **ELEMENT SPECIFICATIONS**

| Hydraulic<br>membrane<br>diameter<br>[mm/mil] | Membrane<br>area<br>[m²/ft²] | Element<br>length L <sub>0</sub><br>[mm/Inch] | Permeate<br>collector inner<br>diameter do<br>[mm/Inch] | Element<br>outer<br>diameter D <sub>0</sub><br>[mm/Inch] |
|---|------------------------------|---|---|--|
| 0.8[31]                                       | 40[430]                      | 1527.5 [60.14]                                | 42.6[1.68]  | 200[7.9]   |
|   |                              |   |   |  |



X-FLOW XF40

# **X-FLOW** XF40 ULTRAFILTRATION MEMBRANE

MEMBRANE ELEMENT DATASHEET

### **OPERATING SPECIFICATIONS**

| Max. trans-<br>membrane<br>pressure<br>Filtration | Max. trans-<br>membrane<br>pressure<br>Backwash | Temp.<br>range   |
|---|---|------------------|
| kPa[psi]  | kPa[psi]  | °C[°F]           |
| 100<br>[14.5]                                     | 200<br>[29]                                     | 0-40<br>[32-104] |

- Max. system pressure: see specifications of membrane housing supplier
- Backwash water should be free of particulates and should be of UF permeate quality or better
- Backwash pumps should preferably be made of non-corroding materials, e.g., plastic or stainless steel. If compressed air is used to pressurize the backwash water, do not allow a two-phase air/water mixture to enter the element
- To avoid mechanical damage, do not subject the membrane module or element to sudden temperature changes, particularly decreasings. Do not exceed 40 °C process temperature. Bring the module or element back to ambient operating temperature slowly (max. value 3 °C/min). Failure to adhere to this guideline can result in irreparable damage

Operation of membrane modules at any combination of maximum limits of pH, concentration, pressure or temperature, during cleaning or production, will influence the membrane lifetime.

## **TECHNICAL SPECIFICATIONS**

# **Weight Specifications**

Dry weight of membrane element ca. 25 kg [55 lbs]

Membrane element filled with water ca. 55 kg [121 lbs]

## **Materials of Construction**

Housing PVC white Flow distributor PVC Potting PU resin Membrane PES/PVP

### **Process Characteristics**

This element type is used for dead-end applications.

### **STORAGE**

New membrane modules can be stored as supplied in the original packaging. The membrane modules contain an aqueous preservation solution of glycerine (20wt%) and sodium metabisulfite (1wt%) to prevent dehydration and control bacterial growth. The membrane modules are packed in plastic bags which are vacuum sealed to keep the moisture in the module. Membrane modules should be stored in a dry, normally ventilated place, away from sources of heat ignition and direct sunlight. Storage temperature should be between 0 and 40 °C. Pentair instructions for transport and storage are to be followed at all times and available upon request. It is recommended to have the membrane modules installed into the UF skids and commissioned as soon as possible. The membrane shelf life is maximum 6 months from the date the modules are announced ready for delivery ex works Pentair warehouse. After expiry of the shelf life all warrantees are null and void.



## X-FLOW BV

P.O. BOX 739, 7500 AS ENSCHEDE, NETHERLANDS WWW.XFLOW.PENTAIR.COM

Note: The information and data contained in this document are based on our general experience and are believed to be correct. They are given in good faith and are intended to provide a guideline for the selection and use of our products. Since the conditions under which our products may be used are beyond our control, this information does not imply any guarantee of final product performance and we cannot accept any liability with respect to the use of our products. The quality of our products is guaranteed under our conditions of sale. Existing intellectual property rights must be observed.

XF40\_DS\_ENG\_V2032 © 2020 Pentair. All Rights Reserved.